

Technical Data Sheet

ZAMAK 430 – Z2 EN1774

Description

In Cinkarna we are also producing the zinc alloy ZAMAK. Zamak has a low melting point, good casting properties, good strength, good handling conditions and possibility for galvanization.

Employment

For pressure casting: furniture gallery, car industry, electro industry, fine mechanic and optic goods, etc.

Technical Data

Chemical composition:	
Al (%)	3,8 – 4,2
Cu (%)	2,7 – 3,3
Mg (%)	0,035 – 0,06
Basic Zn (%)	99,995
Properties:	
Tensile strength	335 Mpa
Stretch breaking point A	5 %
Hardness HB	102
Elastic module	85 Gpa
Spec. weight	6,8 kg/dm ³
Melting point	379 – 389 °C

Packaging

Pallettes a 1000 kg